



Gotya Flat Canvas

Medium-weight Canvas for use in

Car and Truck Seat Covers

Product Information

Features: Water and rot resistant medium-weight canvas, with anti-crush feature specifically designed for use in car and truck seat covers.

Finish: PPC Solid pigment coating on face and back with water and rot resistant; and anti-crush properties.

Fibre content: 52% Polyester, 48% Cotton

Weave: Plain

Mass: Loomstate 405 g/m² (11.9 oz/yd²) Nominal
Coated 505 g/m² (14.9 oz/yd²)

Nominal Width: 190 cm

Roll length: 50 m

Typical Performance:

Strength: Breaking Force (N) (AS2001.2.3A)	Warp: 2900	Weft: 1400
Tearing Force (N) (AS2001.2.10)	Warp: 100	Weft: 65

Water Resistance:

Hydrostatic Pressure (kPa) 4.0
(AS2001.2.17)

Relaxation Shrinkage* (%)	Warp: -3.0	Weft: ± 0.5
----------------------------------	-------------------	------------------------

*The Relaxation Shrinkage test involves fully immersing test specimens in water & soaking for 24hrs followed by an ambient line dry. Results are calculated after 3 x 24hrs soak cycles. Relaxation Shrinkage results provide a good guide as to how the canvas will react to everyday use and are useful in determining the best way to cut and style products.

Colour Fastness:

Light Fastness (AS2001.4.21)	7		
Rub Fastness (AS2001.4.3)	Dry: 3-4	Wet: ± 4	

Total Colour Difference (as compared to nominated standard):

CMC 2:1 DE <1.0

Fabrication Notes:

10 37M PPC will shrink approximately 3.0% in the warp-wise or length-wise direction. Shrinkage in the weft-wise or width-wise direction, however, will be minimal. To minimise the effect of: a) the warp-wise shrinkage and; b) the differential shrinkage exhibited between the length & width of the fabric, the following steps should be taken:

- An allowance for approx. 3.0% shrinkage in the warp/length direction should be made when cutting or sewing any panels together so as to ensure a correct long term fit.
- Panels of fabric should always be cut, stitched or mounted in the same warp/length or weft/width wise direction. Failure to do this will cause uneven shrinkage between panels and over time will most likely result in a puckered/skewed appearance.

Care Instructions:

To obtain maximum life from 10 37M PPC the following should be followed:
10 37M PPC should be kept clean by brushing dry fabric regularly with a soft brush. Can be rinsed with cold water if the need arises, but do not combine the actions of rinsing and brushing.

Do not apply soaps, detergents or other cleaning fluids and keep petrol, kerosene or other similar solvents away from the canvas.